



Technical Data

# HDPE-70

 **coplastomer**<sup>®</sup>

How would you like to change the world?

## Mechanical Properties

Density:	1.02 g/cm <sup>3</sup>	ISO 1183-1A
MFI 190°C/ 2.16 kg:	0.25 g/10min	ISO 1133
Tensile Stress, Yield:	21.32 MPa	ISO 527
Tensile Stress, Break:	21 MPa	ISO 527
Elongation, Break:	14,00%	ISO 527
Young Modulus:	346 MPa	ISO 527
Charpy Impact, 20°C:	67 kJ/m <sup>2</sup>	ISO 179
Hardness of Surface Shore D:	58	ISO 868

The above figures are nominal values only. Tests relating to the application are always necessary.

For more information please contact: [sales@ecoplastomer.eu](mailto:sales@ecoplastomer.eu)