



Technical Data

HDPE-90



How would you like to change the world?

Mechanical Properties

Density:	0.98 g/cm ³	ISO 1183-1A
MFI 190°C/ 2.16 kg:	0.18 g/10min	ISO 1133
Tensile Stress, Yield:	25.46 MPa	ISO 527
Tensile Stress, Break:	23.42 MPa	ISO 527
Elongation, Break:	32,00%	ISO 527
Young Modulus:	436 MPa	ISO 527
Charpy Impact, 20°C:	no break	ISO 179
Hardness of Surface Shore D:	63	ISO 868

The above figures are nominal values only. Tests relating to the application are always necessary.

For more information please contact: sales@ecoplastomer.eu